


Heat Transfer Vinyl -- Metallic

SPECIFICATIONS

Composition	Thickness	Carrier	Certifications
Metallic	0.08~0.12mm	Adhesive polyester	

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
Nylon,polyester, treated fabrics,Leather	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	220~280gf	100~300mm/sec	15s	160°C	Low	Warm/Cold

TRANSFER PROCESS :

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier warm/cold

PRODUCT HIGHLIGHTS :

- Applicable on difficult fabrics (nylon, TNT, leather)
- Wide range of colors

NOTE: We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Uo to 40°C, inside-out	No	Yes (synthetic cycle)	Yes	1~2 year	Between 18°C and 26°C	Away from sunlight and dust	Roll:Vertical Sheet:Level

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.visionsub.com. For further information, please contact our sales office: info@visionsub.com

Shanghai Vision Digital Printing Co.,Ltd
Address
C211 ,Building 100,No.2891, Qilianshan
Nan Rd Pu Tuo District,Shanghai China

Contact
Mobile: +86-18001836806
Hotline: 021-64950449
E-mail: info@visionsub.com



+86-18001836806